

TECHNICAL DATA SHEET

Pondpro2000 is a specially formulate Butyl Liquid Rubber coatings that provides excellent waterproofing and ultraviolet resistance that is demanded by the rv owner. With over a 30-year history of success it is a product that has been trusted by pond repair shops as well as D-I-Y customers. It has excellent adhesion to properly prepared surfaces. It is thermally stable and resists cracking and peeling due to weather extremes. Most recently we have introduced a mildewcide into the formula to deter mold and mildew from growing on the roof. Its unique properties is in the manufacturing process. This product cured by a chemical cross-bond; meaning as the product dried it will chemically bond itself to the roof it is being applied allowing for superior adhesion and longevity.

TYPE OF APPLICATIONS:

- EPDM
- Metal
- Vinyl
- TPO
- Fiberglass
- Hypalon
- Foam

SURFACE PREPARATION:

The surface must be free from oils, moisture soil and another contaminates that may interfere with proper adhesion. Remove loose material from seams and surface. We suggest washing the roof with Dawn or Simply Green and add two cups of bleach for every gallon of water along with your detergent. This will kill any mold spores on your roof.

APPLICATION TEMPERATURES:

For best results, the temperature of the ambient air and the substrate should be within a range of 50°-100°F. however lower temperatures can be utilized if you are using a roller and brush and not airless sprayer to apply.

APPLICATION METHODS:

Product must be mixed with electric drill. We suggest line chalking off your roof into 6ft lengths. Your unit is 8 feet wide so each section is approx. 50 sq ft. Once you are done filling in one of those areas you should be done with a gallon of the product. Pondpro2000 can be applied with a 3/8th inch nap roller and paint brush. For seams that have separated we suggest either our butyl tape or poly fabric. We also offer Skylight-g11 a clear coat that provides extremely effective protection for your fiberglass skylights.

TECHNICAL DATA:

| Coverage | 50 sq ft per gallon |
|----------------------|---------------------|
| Flashpoint | 101°F. |
| Weight (lb./gal.) | 8.95 |
| Solids (% by Weight) | 56%±1% |
| Viscosity @ 78°F | 4800 cps. |
| Drying Time | 2-4 hours |
| Elongation | 400% |
| Tensile Strength | 1200 PSI |
| | |

HANDLING & STORAGE:

Pondpro2000 contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.